



AMORIM

AMORIM CORK COMPOSITES

MATERIAL SPECIFICATION Sheets

Grade: NC775 (239)
Binder: Nitrile Rubber
Cork Granule Size: 0.5-1 mm

Approved by:
Revision: 03
Effective: 01/07/05

Physical Properties:

Test Method	Property	Specification
ASTM D2240	Hardness, Shore A	70 – 85
ASTM F36	Compressibility (400 psi), (%)	15 – 30
ASTM F36	Recovery, (%)	75% min.

Properties after aging:

Test Method	Property	Specification
ASTM F146	Volume Change, ASTM #1, 70 hrs. at 100°C (%)	-10 to +10
	Volume Change, IRM 903, 70 hrs. at 100°C (%)	-10 to +15
	Volume Change, Fuel A, 22 hrs. at RT (%)	-10 to +10